



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 03900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Test Report No.:	2501242-001	
Date Test Report	06-mar-25	Customer Code 00137
Acceptance:	2501242	Dear:
Arrival date sample	03-mar-25	LIMONTA SPA
Start date test	03-mar-25	via Cesare Battisti 15
End date test	06-mar-25	23845 COSTA MASNAGA (LC) Italia
References:		C.a. sig.ra Daniela Marucci
		Phone: +39 031 857471
Sampling Mode:	Sampling by Customer *	

[C] Item:	SOMME
[C] Declared Composition:	37% PC - 30% PL - 18% CO - 13% WV - 2% PA
[C] End use:	furnishing
[C] Typology:	fabric
Return:	no requested

Test Results

Test	Method	U.M.	Result
15066 UPHOLSTERY FURNITURE COMPONENTS: ASSESSMENT OF THE IGNITABILITY BY SMOULDERING CIGARETTE	BS 5852-1:1979		.
Start date test	05/03/2025		
End date test	06/03/2025		
Instrument:	Small Test Rig and burner		
Test carried out on			Cover fabric
Pretreatment carried out			None
Conditioning of sample			20 ± 5 °C, 50 ± 20 % r.h.
Testing temperature and r.h.			19°C - 43% r.h.
Ignition source			source 0 (SMOULDERING CIGARETTE)
TEST RESULT			SAMPLE PASSES THE TEST: PASS
Deviations from the method			None
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			
15076 UPHOLSTERY FURNITURE: ASSESSMENT OF THE IGNITABILITY BY MATCH FLAME	BS 5852-1:1979		.
Start date test	05/03/2025		
End date test	06/03/2025		
Instrument:	Small Test Rig and burner		

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.

Test Report No.: **2501242-001**

Test	Method	U.M.	Result
Test carried out on			Cover fabric
Pretreatment carried out			None
Conditioning of sample			20 ± 5 °C, 50 ± 20 % r.h.
Testing temperature and r.h.			19°C - 43% r.h.
Ignition source			source 1 (MATCH FLAME EQUIVALENT)
TEST RESULT			SAMPLE PASSES THE TEST: PASS
Deviations from the method			None
Annex n.			2F
Details of the test results related to each specimen can be seen in the annex of this test report.			
15066 UPHOLSTERY FURNITURE		UNI EN 1021-1:2014	.
COMPONENTS: ASSESSMENT OF THE IGNITABILITY BY SMOULDERING CIGARETTE			
Start date test	05/03/2025		
End date test	06/03/2025		
Instrument: Small Test Rig and burner			
Test carried out on			Cover fabric
Pretreatment carried out			None
Conditioning of sample			23 ± 2 °C, 50 ± 5 % r.h.
Testing temperature and r.h.			19°C - 43% r.h.
Ignition source			source 0 (SMOULDERING CIGARETTE)
TEST RESULT			SAMPLE PASSES THE TEST: NON IGNITION
Deviations from the method			None
Annex n.			3F
Details of the test results related to each specimen can be seen in the annex of this test report.			
15076 UPHOLSTERY FURNITURE:		UNI EN 1021-2:2006	.
ASSESSMENT OF THE IGNITABILITY BY MATCH FLAME			
Start date test	05/03/2025		
End date test	06/03/2025		
Instrument: Small Test Rig and burner			
Test carried out on			Cover fabric
Pretreatment carried out			None
Conditioning of sample			23 ± 2 °C, 50 ± 5 % r.h.

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 03900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2501242-001**

Test	Method	U.M.	Result
Testing temperature and r.h.			19°C - 43% r.h.
Ignition source			source 1 (MATCH FLAME EQUIVALENT)
TEST RESULT			SAMPLE PASSES THE TEST: NON IGNITION
Deviations from the method			None
Annex n.			4F
Details of the test results related to each specimen can be seen in the annex of this test report.			

The Laboratory Manager

Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
Via Castelnuovo, 3 – 22100 Como Italia
Tel. +39 031331211 Fax +39 0313312149
Amministrazione/Contabilità +39 0313312102-154
P.IVA – C.F. 03900470133
Capitale sociale euro 600.000,00 iv
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Allegato n. 4F al rapporto di prova n. / Annex n. 4F to test report n. 2501052-001

DETTAGLIO DEI RISULTATI DI PROVA DETAILS OF TEST RESULTS

Prova eseguita in conformità a UNI EN 1021-2:2014

Mobili - Verifica dell'accendibilità dei mobili imbottiti – Parte 2 Sorgente di accensione: Fiamma equivalente a fiammifero

Test carried out according to UNI EN 1021-2:2014

Furniture - Assessment of the ignitability of upholstered furniture - Part 2: Ignition source: match flame equivalent

Dettagli di prova / Test Details

Imbottitura / Upholstery filling	Schiuma poliuretanica IGNIFUGA con densità di 35 kg/m ³ , come richiesto dal cliente Fire-retardant polyurethane foam with a density of 35 kg/m ³ , as required by customer
Rivestimento esterno / Outer cover	vedasi descrizione articolo / see article description
Pretrattamento del campione: Sample pretreatment:	il campione NON è stato sottoposto ad alcun pretrattamento, come richiesto dal cliente sample wasn't subjected to any pretreatment, as required by customer

sorgente di ignizione tipo 1: fiamma equivalente a fiammifero ignition source type 1: MATCH	1° test	2° test	3° test	Requisito Requirements
Combustione progressiva pericolosa (SI/NO) Unsafe escalating combustion (YES/NO)	NO	NO	NO	Non presente / None
Durata combustione con fiamma (s) Duration of flames (s)	1	1	2	<120 s
Durata combustione senza fiamma (s) Duration of smoke (s)	16	14	17	< 60 min
Assemblaggio di prova esaurito (SI/NO) Test assembly consumed (YES/NO)	NO	NO	NO	Non presente / None
Combustioni lente o fiamme fino alle estremità (SI/NO) Smoulders or flames to extremities (YES/NO)	NO	NO	NO	Non presente / None
Combustioni lente o fiamme nell'intero spessore (SI/NO) Smoulders or flames through thickness (YES/NO)	NO	NO	NO	Non presente / None
Presenza di fiamme (SI/NO) Evidence of flames (YES/NO)	NO	NO	NO	Non presente / None
Presenza di combustione dopo esame finale (SI/NO) Presence of active smouldering in final examination (YES/NO)	NO	NO	NO	Non presente / None
Risultato / Test result	NON IGNITION	NON IGNITION	NON IGNITION	NON IGNITION

I risultati di prova di cui sopra riguardano esclusivamente l'accendibilità della combinazione di materiali nelle particolari condizioni di prova; essi non sono destinati a essere utilizzati come mezzo di valutazione della pericolosità d'incendio potenziale globale dei materiali nella destinazione d'uso.

La probabilità che i criteri di osservazione indicati corrispondano al vero è pari al 95%.

The above test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test; they are not intended as a mean of assessing the full potential fire hazard of the materials or products.

The probability that the observation criteria mentioned represent the true is equal to 95%.

Il Responsabile Laboratorio
The Laboratory Manager
Fausto Albonico