



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 03900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Test Report No.:	2501242-001	Customer Code 00137
Date Test Report	06-mar-25	Dear:
Acceptance:	2501242	LIMONTA SPA
Arrival date sample	03-mar-25	via Cesare Battisti 15
Start date test	03-mar-25	23845 COSTA MASNAGA (LC) Italia
End date test	06-mar-25	C.a. sig.ra Daniela Marucci
References:		Phone: +39 031 857471
Sampling Mode:	Sampling by Customer *	

[C] Item:	SOMME
[C] Declared Composition:	37% PC - 30% PL - 18% CO - 13% WV - 2% PA
[C] End use:	furnishing
[C] Typology:	fabric
Return:	no requested

Test Results

Test	Method	U.M.	Result
15066 UPHOLSTERY FURNITURE COMPONENTS: ASSESSMENT OF THE IGNITABILITY BY SMOULDERING CIGARETTE	BS 5852-1:1979		.
Start date test	05/03/2025		
End date test	06/03/2025		
Instrument:	Small Test Rig and burner		
Test carried out on			Cover fabric
Pretreatment carried out			None
Conditioning of sample			20 ± 5 °C, 50 ± 20 % r.h.
Testing temperature and r.h.			19°C - 43% r.h.
Ignition source			source 0 (SMOULDERING CIGARETTE)
TEST RESULT			SAMPLE PASSES THE TEST: PASS
Deviations from the method			None
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			
15076 UPHOLSTERY FURNITURE: ASSESSMENT OF THE IGNITABILITY BY MATCH FLAME	BS 5852-1:1979		.
Start date test	05/03/2025		
End date test	06/03/2025		
Instrument:	Small Test Rig and burner		

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.

Test Report No.: **2501242-001**

Test	Method	U.M.	Result
Test carried out on			Cover fabric
Pretreatment carried out			None
Conditioning of sample			20 ± 5 °C, 50 ± 20 % r.h.
Testing temperature and r.h.			19°C - 43% r.h.
Ignition source			source 1 (MATCH FLAME EQUIVALENT)
TEST RESULT			SAMPLE PASSES THE TEST: PASS
Deviations from the method			None
Annex n.			2F
Details of the test results related to each specimen can be seen in the annex of this test report.			
15066 UPHOLSTERY FURNITURE		UNI EN 1021-1:2014	.
COMPONENTS: ASSESSMENT OF THE IGNITABILITY BY SMOULDERING CIGARETTE			
Start date test	05/03/2025		
End date test	06/03/2025		
Instrument: Small Test Rig and burner			
Test carried out on			Cover fabric
Pretreatment carried out			None
Conditioning of sample			23 ± 2 °C, 50 ± 5 % r.h.
Testing temperature and r.h.			19°C - 43% r.h.
Ignition source			source 0 (SMOULDERING CIGARETTE)
TEST RESULT			SAMPLE PASSES THE TEST: NON IGNITION
Deviations from the method			None
Annex n.			3F
Details of the test results related to each specimen can be seen in the annex of this test report.			
15076 UPHOLSTERY FURNITURE:		UNI EN 1021-2:2006	.
ASSESSMENT OF THE IGNITABILITY BY MATCH FLAME			
Start date test	05/03/2025		
End date test	06/03/2025		
Instrument: Small Test Rig and burner			
Test carried out on			Cover fabric
Pretreatment carried out			None
Conditioning of sample			23 ± 2 °C, 50 ± 5 % r.h.

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 03900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2501242-001**

Test	Method	U.M.	Result
Testing temperature and r.h.			19°C - 43% r.h.
Ignition source			source 1 (MATCH FLAME EQUIVALENT)
TEST RESULT			SAMPLE PASSES THE TEST: NON IGNITION
Deviations from the method			None
Annex n.			4F
Details of the test results related to each specimen can be seen in the annex of this test report.			

The Laboratory Manager

Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
Via Castelnuovo, 3 – 22100 Como Italia
Tel. +39 031331211 Fax +39 0313312149
Amministrazione/Contabilità +39 0313312102-154
P.IVA – C.F. 03900470133
Capitale sociale euro 600.000,00 iv
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Allegato n. 2F al rapporto di prova / Annex n. 2F to test report n. 2501242-001

DETTAGLIO DEI RISULTATI DI PROVA DETAILS OF TEST RESULTS

Prova eseguita in conformità a BS 5852-Parte1:1979 + Scheda 5, Parte 1 'Match Test' della "Regolamentazione su mobili e arredi (Incendio) (Sicurezza) 1988 - Statutory Instruments 1324 e successivi emendamenti"

Valutazione dell'infiammabilità di mobili imbottiti mediante articoli per fumatori come sorgenti di ignizione. Sorgente di accensione: FIAMMA EQUIVALENTE A FIAMMIFERO

Test carried out according to BS 5852-Part1:1979 + Schedule 5, Part 1 'The Match Test' of Furniture and Furnishing (Fire) (Safety) Regulations 1988 S.I. 1324 and next amendments

Fire test for furniture - Part 1. Methods of test for the ignitability by smokers' materials of upholstered composites for seating - Ignition source: MATCH TEST

Materiali dell'assemblaggio / Materials of test assembly:	
Imbottitura / Upholstery filling	Schiuma poliuretanica NON IGNIFUGA con densità di 21 kg/m ³ , come previsto dallo Statutory Instruments <i>NON fire-retardant polyurethane foam with a density of 21 kg/m³, as required by the Statutory Instruments</i>
Rivestimento esterno / Outer cover	vedasi descrizione articolo / see article description
Pretrattamento del campione: Sample pretreatment:	il campione NON è stato sottoposto ad alcun pretrattamento, come richiesto dal cliente <i>sample wasn't subjected to any pretreatment, as required by customer</i>

sorgente di ignizione tipo 1: fiamma equivalente a fiammifero <i>ignition source type 1: MATCH FLAME EQUIVALENT</i>	1° test Destra / Right	2° test Sinistra / Left	Requisito Requirements
Durata combustione sorgente – Duration of ignition source (s)	20	20	
Tempi comb. con fiamma dalla rimozione della sorgente <i>Time of flaming after removal of the burner (s)</i>	2	1	<120 s
Durata combustione senza fiamma / Duration of smoke (s)	15	13	< 60 min
Combustione pericolosa con o senza fiamma * <i>Escalating smouldering/flaming combustion behaviour</i>	NO	NO	Non presente None
Fusione del campione (SI/NO) / Sample melting (YES/NO)	SI/YES	SI/YES	-
Gocciolamento del campione (SI/NO) / Sample dripping (YES/NO)	NO	NO	-
Carbonizzazione del campione (SI/NO) / Sample charring (YES/NO)	SI/YES	SI/YES	-
Combustione progressiva osservata dopo l'esame finale <i>Progressive smouldering observed after the final examination</i>	NO	NO	Non presente None
TEST RESULT	PASS	PASS	PASS

Nota: la combustione si è sviluppata in modo pericoloso tale da rendere necessaria una estinzione attiva

Note: the combustion developed so that forcible extinction was required

I risultati di prova di cui sopra riguardano esclusivamente l'accendibilità della combinazione di materiali nelle particolari condizioni di prova; essi non sono destinati a essere utilizzati come mezzo di valutazione della pericolosità d'incendio potenziale globale dei materiali nella destinazione d'uso
The above test result relate only to the ignitability of the combination of upholstery composites under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials or products

La probabilità che i criteri di osservazione indicati corrispondano al vero è pari al 95%.

The probability that the observation criteria mentioned represent the true is equal to 95%.

Il Responsabile Laboratorio
The Laboratory Manager
Fausto Albonico