



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 03900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com
www.textilecomo.com

Test Report No.:

2406888-001

Date Test Report **11-dic-24**

Acceptance: **2406888**

Arrival date sample **28-nov-24**

Start date test **28-nov-24**

End date test **10-dic-24**

References:

Sampling Mode: Sampling by Customer

Customer Code 00137

Dear:

LIMONTA SPA

via Cesare Battisti 15

23845 COSTA MASNAGA (LC) Italia

C.a. sig.ra Daniela Marucci

Phone: +39 031 857471

[C] Item: **VIDAR**
[C] Declared Composition: **100% Polyester**
[C] End use: **furnishing**
[C] Typology: **fabric**
Return: **no requested**

Test Results

Test	Method	U.M.	Result
15046 PREPARATION OF MATERIALS FOR BURNING BEHAVIOUR TESTS: 5 WASHING CYCLES	UNI 9176:1998 - met A		.
Start date test	02/12/2024		
End date test	04/12/2024		
Instrument: WASHING-MACHINE ELECTROLUX WASCATOR mod. FOM 71 CLS			
PROCEDURE: The sample has been submitted to 5 washing cycles in a solution of water and detergent; after each washing, the sample has been dried in a drying oven at the temperature of 60° C for 2 hours. Washing temperature: 40° C degrees Ratio material/solution: 1:3			
After all washing cycles, the sample has been ironed and submitted to fire test.			
15016 REACTION TO FIRE BY APPLYING A SMALL FLAME: FLAME ON BOTH SURFACES	UNI 8456: 1987 + A1:1996		.
Start date test	09/12/2024		
End date test	10/12/2024		
Instrument: Flammability Chamber - Noselab			
Pretreatment carried out			sample was subjected to 5 washing cycles, as above described
Number of tests specimens			10
Time of application of flame:	s		12
CATEGORY ASSIGNED TO TESTED MATERIAL			FIRST CATEGORY
Deviations from the method			None
Legislative references			.
Other references: D.M. 26 June 1984 - D.M. dell'Interno 3 September 2001			
Test is not valid for homologation			
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.
This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.
[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 03900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com

Test Report No.: **2406888-001**

Test	Method	U.M.	Result
15236 REACTION TO FIRE OF MATERIAL CAN BE HIT BY FLAME WITH RADIANT HEATING	UNI 9174:1987 + A1:1996		.
Start date test	09/12/2024		
End date test	10/12/2024		
Instrument:	Radiant Pannel - ATS FAAR		
Pretreatment carried out			sample was subjected to 5 washing cycles, as above described
Specimens position:			to the wall
Preparation of the sample:			simple
Number of tests specimens			8
CATEGORY ASSIGNED TO TESTED MATERIAL			FIRST CATEGORY
Deviations from the method			.
Because of the fabric lack, the test was carried out on n. 8 specimens instead of n.12 as previewed by the standard method; this deviation could affect the test result and therefore the Test Laboratory declines all responsibility.			
Annex n.			2F
Details of the test results related to each specimen can be seen in the annex of this test report.			
15906 COMBUSTIBLE MATERIALS CLASSIFICATION	UNI 9177:1987		.
SAMPLE MEETS THE CLASS 1 REQUIREMENTS This classification follows from the results of the tests executed according to UNI 8456 and UNI 9174, as above reported.			

The Laboratory Manager
Fausto Albonico

END OF REPORT

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.
This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.
[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.

Annex n. 2F to test report n. 2406888-001

DETAILS OF TEST RESULTS

Test executed according to UNI 9174 (1987) + UNI 9174/A1/96:
Fire reaction of materials under flame action with radiant heat

Type: anisotropic fabric with different faces

specimen direction	Average rate of spread of flame		Post-glow time		Extent of damage		Drip	
	speed (mm/min)	level	time (s)	level	length (mm)	level	time (s)	level
warp *	N.R. ⁽¹⁾	1	0	1	250	1	Parts turned off	1
warp *	N.R. ⁽¹⁾	1	0	1	300	1	Parts turned off	1
warp *	Fabric lack							
warp **	N.R. ⁽¹⁾	1	0	1	300	1	Parts turned off	1
warp **	N.R. ⁽¹⁾	1	0	1	300	1	Parts turned off	1
warp **	Fabric lack							
weft *	N.R. ⁽¹⁾	1	0	1	300	1	Parts turned off	1
weft *	N.R. ⁽¹⁾	1	0	1	350	1	Parts turned off	1
weft *	Fabric lack							
weft **	N.R. ⁽¹⁾	1	0	1	300	1	Parts turned off	1
weft **	N.R. ⁽¹⁾	1	0	1	350	1	Parts turned off	1
weft **	Fabric lack							
Total level:		1		1		1		1
Multiplier factor:		2		1		2		1
Total:		2		1		2		1

* = face of fabric ** = back of fabric

(1) fabric melts as soon as it is placed and there is no flame. The times and relative speeds are therefore not measurable.

Combined total Levels for the multiplication factor:

CATEGORY ASSIGNED TO THE SAMPLE: FIRST CATEGORY



Centro Tessile Serico Sostenibile Srl
Via Castelnuovo, 3 – 22100 Como Italia
Tel. +39 031331211 Fax +39 0313312149
Amministrazione/Contabilità +39 0313312102-154
P.IVA – C.F. 03900470133
Capitale sociale euro 600.000,00 iv
mailbox@textilecomo.com
www.textilecomo.com

Annex n. 2F to test report n. 2406888-001

LEVELS OF CONDUCT OF THE PRODUCTS (ref. UNI 9174:1987)

Rate of spread of flame

Level 1: speed can not be measured because the flame does not reach the 150 mm (third goal).

Level 2: propagation velocity less than or equal to 30 mm / min.

Level 3: velocity of propagation greater than 30 mm / min.

Damaged area

Level 1: less than 300 mm.

Level 2: between 350 mm and 600 mm.

Level 3: greater than 600 mm.

Post-glow

Level 1: less than or equal to 180 s.

Level 2: greater than 180 seconds but less than or equal to 360 s.

Level 3: greater than 360 s.

Drip

Level 1: absent or with any droplets and / or chipping off at the time of contact with the bottom of the combustion chamber

Level 2: drops and / or loose parts are inflamed, but off within 3 seconds

Level 3: drops and / or loose parts inflamed for more than 3 seconds

Special cases

If the material burns in the presence of flame over 60 min, it is assumed that the damaged area is level 3. The speed of propagation of the flame is calculated between 100 mm and the last goal achieved by the flame itself. The drip and glow are those already detected earlier. In the case in which the speed of propagation of the flame is greater than or equal to 200 mm / min and the damaged area is greater than or equal to 650 mm the material is placed in the last category.

For the materials in the test position to the wall, in the case in which the speed of propagation of the flame is greater than 30 mm / min and the damaged area is less than or equal to 200 mm, is conventionally attaches the level 2 at the speed of propagation of the flame. For textile materials which can be hit by the fire on both faces (in the test position to the wall) in the case in which the speed of propagation of the flame is greater than 30 mm / min and in the case in which the damaged area is less than or equal to 300 mm is attached conventionally to the speed of propagation of the flame level 2.

Note:

The time of post-glow is detected always starting at 300 mm from the edge of the specimen closest to the radiant panel.

The damaged area is detected by measuring the length between the edge of the specimen closest to the radiant panel and the ultimate goal achieved by the flame

CATEGORIES IN RELATION TO THE AMOUNT OF LEVELS FOR MULTIPLYING FACTOR

Specimen "TO THE WALL"

CATEGORIES	Combined total Levels for the multiplication factor
I	6-8
II	9-12
III	13-15
IV	16-18

The Laboratory Manager
Fausto Albano



Centro Tessile Serico Sostenibile Srl
 Via Castelnuovo, 3 – 22100 Como Italia
 Tel. +39 031331211 Fax +39 0313312149
 Amministrazione/Contabilità +39 0313312102-154
 P.IVA – C.F. 03900470133
 Capitale sociale euro 600.000,00 iv
mailbox@textilecomo.com
www.textilecomo.com

Annex n. 1F to test report n. 2406888-001

DETAILS OF TEST RESULTS

Test executed according to UNI 8456:1987

Combustible materials which can be hit by flame on both surface – Reaction to fire by applying a small flame

specimen direction	Post-combustion time		Post-glowing time		Extent of damage		Dripping	
	time (s)	level	time (s)	level	length (mm)	level	time (s)	level
warp	0	1	0	1	80	1	absent	1
warp	0	1	0	1	88	1	absent	1
warp	0	1	0	1	66	1	absent	1
warp	0	1	0	1	74	1	absent	1
warp	0	1	0	1	79	1	absent	1
weft	0	1	0	1	62	1	absent	1
weft	0	1	0	1	90	1	absent	1
weft	0	1	0	1	81	1	absent	1
weft	0	1	0	1	86	1	absent	1
weft	0	1	0	1	69	1	absent	1
Total level::		1		1		1		1
Multiplier factor:		2		1		2		1
Total:		2		1		2		1

Total of all levels: 6

CATEGORY ASSIGNED TO THE SAMPLE: FIRST CATEGORY



Centro Tessile Serico Sostenibile Srl
Via Castelnuovo, 3 – 22100 Como Italia
Tel. +39 031331211 Fax +39 0313312149
Amministrazione/Contabilità +39 0313312102-154
P.IVA – C.F. 03900470133
Capitale sociale euro 600.000,00 iv
mailbox@textilecomo.com
www.textilecomo.com

Annex n. 1F to test report n. 2406888-001

LEVELS OF BEHAVIOR OF MATERIALS (REF. UNI 8456:1987)

1 - Time of post-combustion

Level 1: less than or equal to 5 s

Level 2: more than 5 seconds, but less than or equal to 60 s

Level 3: greater than 60 s

2 - Time after-glow

Level 1: less than or equal to 10 s

Level 2: greater than 10 s, but less than or equal to 60 s

Level 3: greater than 60 s

3 - Zone damaged

Level 1: less than or equal to 150 mm

Level 2: greater than 150 mm, but less than or equal to 200 mm

Level 3: greater than 200 mm

4 - Dripping

Level 1: absent or with any droplets and / or detached parts turned off at the time of contact with the bottom of the combustion chamber

Level 2: drops and / or loose parts are inflamed, but off within 3 s

Level 3: drops and / or loose parts inflamed for more than 3 s

If a product burns completely in a time less than or equal to 17 s from the beginning of the test (this time includes the 12 s of ignition with flame and the 5 s post-combustion), its behavior is attributed last category.

When the product burns over 10 min, it is assumed that the damaged area is level 3.

CATEGORIES ACCORDING OF TOTAL OF LEVELS

CATEGORIES	TOTAL OF LEVELS
I	6-8
II	9-12
III	13-15
IV	16-19

The Laboratory Manager
Fausto Albani
