

| | | |
|---------------------|------------------------|---------------------------------|
| Test Report No.: | 2500169-001 | |
| Date Test Report | 17-gen-25 | Customer Code 00137 |
| Acceptance: | 2500169 | Dear: |
| Arrival date sample | 15-gen-25 | LIMONTA SPA |
| Start date test | 15-gen-25 | via Cesare Battisti 15 |
| End date test | 17-gen-25 | 23845 COSTA MASNAGA (LC) Italia |
| References: | | C.a. sig.ra Daniela Marucci |
| | | Phone: +39 031 857471 |
| Sampling Mode: | Sampling by Customer * | |

| | |
|---------------------------|--|
| [C] Item: | BAENA |
| [C] Declared Composition: | 35% PC - 30% WV - 25% PL - 10% CO |
| [C] End use: | furnishing |
| [C] Typology: | fabric |
| Return: | no requested |

Test Results

| Test | Method | U.M. | Result |
|---|---------------------------|------|----------------------------------|
| 15066 UPHOLSTERY FURNITURE COMPONENTS: ASSESSMENT OF THE IGNITABILITY BY SMOULDERING CIGARETTE | BS 5852-1:1979 | | . |
| Start date test | 16/01/2025 | | |
| End date test | 17/01/2025 | | |
| Instrument: | Small Test Rig and burner | | |
| Test carried out on | | | Cover fabric |
| Pretreatment carried out | | | None |
| Conditioning of sample | | | 20 ± 5 °C, 50 ± 20 % r.h. |
| Testing temperature and r.h. | | | 17°C - 47% r.h. |
| Ignition source | | | source 0 (SMOULDERING CIGARETTE) |
| TEST RESULT | | | SAMPLE PASSES THE TEST: PASS |
| Deviations from the method | | | None |
| Annex n. | | | 1F |
| Details of the test results related to each specimen can be seen in the annex of this test report. | | | |
| 15076 UPHOLSTERY FURNITURE: ASSESSMENT OF THE IGNITABILITY BY MATCH FLAME | BS 5852-1:1979 | | . |
| Start date test | 16/01/2025 | | |
| End date test | 17/01/2025 | | |
| Instrument: | Small Test Rig and burner | | |

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.

Test Report No.: **2500169-001**

| Test | Method | U.M. | Result |
|--|------------|--------------------|---|
| Test carried out on | | | Cover fabric |
| Pretreatment carried out | | | None |
| Conditioning of sample | | | 20 ± 5 °C, 50 ± 20 % r.h. |
| Testing temperature and r.h. | | | 17°C - 47% r.h. |
| Ignition source | | | source 1 (MATCH FLAME EQUIVALENT) |
| TEST RESULT | | | SAMPLE PASSES THE TEST: PASS |
| Deviations from the method | | | None |
| Annex n. | | | 2F |
| Details of the test results related to each specimen can be seen in the annex of this test report. | | | |
| 15066 UPHOLSTERY FURNITURE | | TB 117:2013 | . |
| COMPONENTS: ASSESSMENT OF THE IGNITABILITY BY SMOULDERING CIGARETTE | | | |
| Start date test | 16/01/2025 | | |
| End date test | 17/01/2025 | | |
| Instrument: Mini Mock Up Tester | | | |
| Test carried out on | | | Cover fabric |
| Pretreatment carried out | | | None |
| Conditioning of sample | | | 21 ± 3 °C, <55% r.h. |
| Testing temperature and r.h. | | | 17°C - 47% r.h. |
| Ignition source | | | NON filtered standard cigarette SRM 1196 |
| TEST RESULT | | | PASS |
| Deviations from the method | | | None |
| Annex n. | | | 3F |
| Details of the test results related to each specimen can be seen in the annex of this test report. | | | |

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 003900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2500169-001**

| Test | Method | U.M. | Result |
|------|--------|------|--------|
|------|--------|------|--------|

The Laboratory Manager

Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
Via Castelnuovo, 3 – 22100 Como Italia
Tel. +39 031331211 Fax +39 0313312149
Amministrazione/Contabilità +39 0313312102-154
P.IVA – C.F. 03900470133
Capitale sociale euro 600.000,00 iv
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Allegato n. 2F al rapporto di prova / Annex n. 2F to test report n. 2500169-001

DETTAGLIO DEI RISULTATI DI PROVA DETAILS OF TEST RESULTS

Prova eseguita in conformità a BS 5852-Parte1:1979 + Scheda 5, Parte 1 'Match Test' della "Regolamentazione su mobili e arredi (Incendio) (Sicurezza) 1988 - Statutory Instruments 1324 e successivi emendamenti"

Valutazione dell'infiammabilità di mobili imbottiti mediante articoli per fumatori come sorgenti di ignizione. Sorgente di accensione: FIAMMA EQUIVALENTE A FIAMMIFERO

Test carried out according to BS 5852-Part1:1979 + Schedule 5, Part 1 'The Match Test' of Furniture and Furnishing (Fire) (Safety) Regulations 1988 S.I. 1324 and next amendments

Fire test for furniture - Part 1. Methods of test for the ignitability by smokers' materials of upholstered composites for seating - Ignition source: MATCH TEST

| Materiali dell'assemblaggio / Materials of test assembly: | |
|--|---|
| Imbottitura / Upholstery filling | Schiuma poliuretanica NON IGNIFUGA con densità di 21 kg/m ³ , come previsto dallo Statutory Instruments <i>NON fire-retardant polyurethane foam with a density of 21 kg/m³, as required by the Statutory Instruments</i> |
| Rivestimento esterno / Outer cover | vedasi descrizione articolo / see article description |
| Pretrattamento del campione: Sample pretreatment: | il campione NON è stato sottoposto ad alcun pretrattamento, come richiesto dal cliente <i>sample wasn't subjected to any pretreatment, as required by customer</i> |

| sorgente di ignizione tipo 1: fiamma equivalente a fiammifero <i>ignition source type 1: MATCH FLAME EQUIVALENT</i> | 1° test Destra / Right | 2° test Sinistra / Left | Requisito Requirements |
|--|---------------------------|----------------------------|---------------------------|
| Durata combustione sorgente – Duration of ignition source (s) | 20 | 20 | |
| Tempi comb. con fiamma dalla rimozione della sorgente <i>Time of flaming after removal of the burner (s)</i> | 1 | 0 | <120 s |
| Durata combustione senza fiamma / Duration of smoke (s) | 21 | 20 | < 60 min |
| Combustione pericolosa con o senza fiamma * <i>Escalating smouldering/flaming combustion behaviour</i> | NO | NO | Non presente None |
| Fusione del campione (SI/NO) / Sample melting (YES/NO) | NO | NO | - |
| Gocciolamento del campione (SI/NO) / Sample dripping (YES/NO) | NO | NO | - |
| Carbonizzazione del campione (SI/NO) / Sample charring (YES/NO) | SI/YES | SI/YES | - |
| Combustione progressiva osservata dopo l'esame finale <i>Progressive smouldering observed after the final examination</i> | NO | NO | Non presente None |
| TEST RESULT | PASS | PASS | PASS |

I risultati di prova di cui sopra riguardano esclusivamente l'accendibilità della combinazione di materiali nelle particolari condizioni di prova; essi non sono destinati a essere utilizzati come mezzo di valutazione della pericolosità d'incendio potenziale globale dei materiali nella destinazione d'uso

The above test result relate only to the ignitability of the combination of upholstery composites under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials or products

La probabilità che i criteri di osservazione indicati corrispondano al vero è pari al 95%.

The probability that the observation criteria mentioned represent the true is equal to 95%.

Il Responsabile Laboratorio
The Laboratory Manager
Fausto Albonico