

**PET APPAREL, HATS, BOW TIE**

Number: BURL-122  
Creation Date: 11/1/2021  
Revision Date: 9/16/2022  
Created by: Legal Dept.

TEST DESCRIPTION	REGULATION/TEST METHOD	REQUIREMENTS
<b>MANDATORY</b>		
Label Verification	F.P. & L. Act (16 CFR – 500) OR NIST Uniform Laws and Regulations Handbook 130	Manufacturer, packer, or distributor’s name & address (city, state & zip)
		Product Identification
		Net quantity of contents shall be expressed in terms of weight or mass, measure, numerical count, or combination so as to give accurate information to facilitate consumer comparison (U.S. and metric units).
Fiber Labeling	Fiber Content 16 CFR 303/16 CFR 300	Must be visible at point of sale & must comply with regulations
	RN# or WPL # or Mfr. Name	Verify presence and must comply with the Textile Fiber Product Identification Act or Wool Products Labeling Act.
	Care Label (if indicated on labeling)	Comply with regulations (Care Labeling Rule)
Country of Origin Marking	19 CFR 134.11	Shall indicate country of origin legibly, permanently, and incomparable size and close proximity to any mention of country other than country in which the article was manufactured or produced. Must be visible at point of purchase.
Imitation Leather	16 CFR 24	Non-leather material that appear as leather must be disclosed in label (e.g., Not Leather, Simulated Leather, Vinyl, Vinyl Coated Fabric, Plastic, etc.). Form of disclosures: on a tag, label, or card attached to the product, and should be affixed so as to remain on or attached to the product until received by the consumer purchaser.
Pentachlorothiophenol (PCTP)	Environmental Protection Agency, 86 FR 894, Final Rule, 40 CFR Part 751, Subpart E	≤ 1 % (10000 mg/kg)
Hexachlorobutadiene (HCBD)	Environmental Protection Agency, 86 FR 894, Final Rule, 40 CFR Part 751, Subpart E	Prohibited
California Prop 65	Warning label or applicable testing	In lieu of warning label, product should meet all applicable Prop 65 requirements.
Total heavy metals in packaging	Toxics in Packaging Clearinghouse (TPCH)	Packaging shall not contain the sum of mercury, cadmium, lead and chromium (VI) in concentration above 0.01% by weight. Sum of Phthalates: ≤ 100 mg/kg PFAS: Not detected
Flame Retardants	Various state laws	Products claimed with flame retardant treatment shall meet all applicable requirements.

Plastic Bag Warnings	Various state laws	Plastic bags with a thickness of less than 1 mil (0.001 inch) having an opened end larger than 5 inches in diameter shall contain the following warning statement or equivalent: <b>WARNING: To avoid danger of suffocation, keep this plastic bag away from babies and children. Do not use this bag in cribs, beds, carriages or playpens. This bag is not a toy.</b>									
<b>NON-MANDATORY (QUALITY &amp; PERFORMANCE)</b>											
Colorfastness to Crocking	AATCC 8 Year: 2016	Minimums for Dyed Textiles and Synthetic Leather: Dry: 4.0 Wet: 3.0 Minimums for Print Textiles, Denim Textiles and Genuine or Suede Leather: Dry: 3.0 Wet: 2.0									
Colorfastness to Chlorine Bleach	AATCC TS-001	Color change: Min. Grade 4									
Colorfastness to Non-Chlorine Bleach	AATCC TS-001	Color change: Min. Grade 4									
Dimensional Stability to Laundering – Woven (3x)	AATCC 150	<table style="margin-left: auto; margin-right: auto;"> <thead> <tr> <th></th> <th>% Length</th> <th>% Width</th> </tr> </thead> <tbody> <tr> <td>Basic – Natural</td> <td>5</td> <td>X 5</td> </tr> <tr> <td>Basic - Synthetic</td> <td>3</td> <td>X 3</td> </tr> </tbody> </table>		% Length	% Width	Basic – Natural	5	X 5	Basic - Synthetic	3	X 3
	% Length	% Width									
Basic – Natural	5	X 5									
Basic - Synthetic	3	X 3									
Dimensional Stability to Laundering – Knits (3x)	AATCC 150	<table style="margin-left: auto; margin-right: auto;"> <thead> <tr> <th></th> <th>% Length</th> <th>% Width</th> </tr> </thead> <tbody> <tr> <td></td> <td>5</td> <td>X 7</td> </tr> </tbody> </table>		% Length	% Width		5	X 7			
	% Length	% Width									
	5	X 7									
Appearance after Home Laundering (3x)	AATCC TM135/150	No open raveling, open seams, or tufting damage. No obvious defects/observations affecting the end product performance/appearance. Color change: Print and Pigment Min Grade 3.5 Other Min Grade 4.0 Color staining: Dark color, pigment Min Grade 3.0 Others Min Grade 3.5 Self staining Min Grade 4.5 List all observations									
Durability of Zipper	Actual Use	500 cycles									
Resistance to Corrosion (for metal component only)	ASTM B117 (mod.)	No major discolorations in appearance or rusting after exposure to 1% salt solution for 24 hours. (mod. = apply 1% salt solution)									
Colorfastness to Accelerated Laundering	AATCC 61	Color change: Print and Pigment Min Grade 3.5 Other Min Grade 4.0 Color staining: Dark color, pigment Min Grade 3.0 Others Min Grade 3.5 Self staining Min Grade 4.5									